# Nylon Tubing


# *Series T/TIA*




RoHS

## For general pneumatic tubing, Nylon tubing

## Max. Operating Pressure




How to measure the minimum bending radius.




At a temperature of 20°C, bend the tubing into a U shape. Fix one end and gradually move the other end closer. Measure 2R at the point where the outside diameter's rate of change is 10%.

## Model

● — 20 m roll □ — 100 m roll (T1613 is reel.)

| | Tubing size | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | Metric size (Series T) | | | | | | | | Inch size (Series TIA) | | | | |
| Model | T0425 | T0403 | T0604 | T0645 | T0806 | T1075 | T1209 | T1613 | TIA01 | TIA05 | TIA07 | TIA11 | TIA13 |
| Tubing O.D. (mm) | 4 | 4 | 6 | 6 | 8 | 10 | 12 | 16 | 3.18 | 4.76 | 6.35 | 9.53 | 12.7 |
| Tubing I.D. (mm) | 2.5 | 3 | 4 | 4.5 | 6 | 7.5 | 9 | 13 | 2.18 | 3.48 | 4.57 | 6.99 | 9.56 |
| Black (B) | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● |
| White (W) | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● |
| Red (R) | ● | | ● | | ● | ● | ● | | | | | | |
| Blue (BU) | ● | | ● | | ● | ● | ● | | | | | | |
| Yellow (Y) | ● | | ● | | ● | ● | ● | | | | | | |
| Green (G) | ● | | ● | | ● | ● | ● | | | | | | |
| | 5⁄32" | | | | 5⁄16" | | | | Nominal size (inch) | | | | |
| | | | | | | | | | 1⁄8" | 3⁄16" | 1⁄4" | 3⁄8" | 1⁄2" |
| | | | | | | | | | Nominal size (mm) | | | | |
| | | | | | | | | | 3.2 | | | | |

## Specifications

| Fluid | | Air/Water | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Max. operating pressure (MPa) Note 1) | 20°C or less | 3.3 | 2.0 | 3.0 | 2.0 | 2.0 | 2.0 | 2.0 | 1.6 | 2.3 | 2.3 | 2.3 | 2.3 | 2.3 |
| | 40°C | 2.3 | 1.4 | 2.1 | 1.4 | 1.4 | 1.4 | 1.4 | 1.1 | 1.6 | 1.6 | 1.6 | 1.6 | 1.6 |
| | 60°C | 1.65 | 1.0 | 1.5 | 1.0 | 1.0 | 1.0 | 1.0 | 0.8 | 1.15 | 1.15 | 1.15 | 1.15 | 1.15 |
| | 80°C | 1.35 | 0.8 | 1.25 | 0.8 | 0.8 | 0.8 | 0.8 | 0.65 | 0.95 | 0.95 | 0.95 | 0.95 | 0.95 |
| | 100°C | 1.2 | 0.75 | 1.1 | 0.75 | 0.75 | 0.75 | 0.75 | 0.6 | 0.85 | 0.85 | 0.85 | 0.85 | 0.85 |
| Applicable fittings Note 1) Note 2) | | One-touch fittings, Insert fittings, Self-align fittings, Miniature fittings | | | | | | | | | | | | |
| Min. bending radius (mm) Note 3) | Min. bending radius | 13 | 20 | 24 | 30 | 40 | 50 | 60 | 100 | 15 | 25 | 30 | 50 | 65 |
| | Bending value (Reference) | 10 | 15 | 18 | 23 | 30 | 40 | 45 | 75 | 12 | 20 | 23 | 40 | 48 |
| Operating temperature Note 1) | | –40 to +100°C, Water: 0 to +70°C (No freezing) | | | | | | | | | | | | |
| Material | | Nylon 12 | | | | | | | | | | | | |

Note 1) Be sure to operate under the maximum operating pressure conditions using the lower maximum operating specification of either the tubing or fittings.

Note 2) Mount an inner sleeve when using metal One-touch fittings in high-temperature environments of 60°C or more. Use self-align fittings at a temperature of 60°C or less.

Note 3) The minimum bending radius is the representative value measured as shown in the left figure.
- Use a tube above the recommended minimum bending radius.
- The tubing may be bent if used under the recommended minimum bending radius. Therefore, refer to the refraction value and make sure that the tubing is not bent or flattened.
- Please note that the refraction value is not warranted because of the value when 2R is measured by the method in the left figure if the tubing is bent or flattened, etc.

# ⚠ Precautions

## ⚠Caution

1. Applicable for general industrial water. Please consult with SMC if using other kinds of fluid. Surge pressure must be under the max. operating pressure. If the surge pressure exceeds the maximum operating pressure, it will result in damage to fittings and tubes.
2. Please exercise caution when using this item in a clean room. There is a possibility of plasticizer and other materials precipitating on the tube surface and detracting from the cleanliness level of the room.

## How to Order

**T0425** **B** – **20**

**Tubing model**

**Color**

| Symbol | Color |
|---|---|
| B | Black (Translucent) |
| W | White (Material color) |
| R | Red (Translucent) |
| BU | Blue (Translucent) |
| Y | Yellow (Translucent) |
| G | Green (Translucent) |

**Length per roll**

| Symbol | Length |
|---|---|
| 20 | 20 m roll |
| 100 | 100 m roll |


# Soft Nylon Tubing
# *Series TS/TISA*



RoHS

**For general pneumatic tubing**
**Pliable soft nylon tubing**

## Max. Operating Pressure




## Model

● — 20 m roll □ — 100 m roll (TS1612 is reel.)

| | Tubing size | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|
| | Metric size (Series TS) | | | | | | Inch size (Series TISA) | | | | |
| Model | TS0425 | TS0604 | TS0806 | TS1075 | TS1209 | TS1612 | TISA01 | TISA05 | TISA07 | TISA11 | TISA13 |
| Tubing O.D. (mm) | 4 | 6 | 8 | 10 | 12 | 16 | 3.18 | 4.76 | 6.35 | 9.53 | 12.7 |
| Tubing I.D. (mm) | 2.5 | 4 | 6 | 7.5 | 9 | 12 | 2.18 | 3.48 | 4.57 | 6.99 | 9.56 |
| Black (B) | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● |
| White (W) | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● | ● |
| Red (R) | ● | ● | ● | ● | ● | | ● | ● | ● | ● | ● |
| Blue (BU) | ● | ● | ● | ● | ● | | ● | ● | ● | ● | ● |
| Yellow (Y) | ● | ● | ● | ● | ● | | ● | ● | ● | ● | ● |
| Green (G) | ● | ● | ● | ● | ● | | ● | ● | ● | ● | ● |
| Nominal size (inch) | 5/32" | 5/16" | | | | | 1/8" | 3/16" | 1/4" | 3/8" | 1/2" |
| Nominal size (mm) | | | | | | | 3.2 | | | | |

## Specifications

| Fluid | | Air/Water Note 1) | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| Max. operating pressure MPa Note 2) | 20°C or less | 2.0 | 1.7 | 1.3 | 1.3 | 1.3 | 1.3 | 1.3 | 1.3 | 1.3 | 1.3 | 1.3 |
| | 40°C | 1.4 | 1.2 | 0.9 | 0.9 | 0.9 | 0.9 | 0.9 | 0.9 | 0.9 | 0.9 | 0.9 |
| | 60°C | 1.0 | 0.85 | 0.65 | 0.65 | 0.65 | 0.65 | 0.65 | 0.65 | 0.65 | 0.65 | 0.65 |
| | 80°C | 0.8 | 0.65 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 |
| | 100°C | 0.6 | 0.45 | 0.35 | 0.35 | 0.35 | 0.4 | 0.35 | 0.35 | 0.35 | 0.35 | 0.35 |
| Applicable fittings Note 2) 3) | | One-touch fittings, Insert fittings, Self-align fittings, Miniature fittings | | | | | | | | | | |
| Min. bending radius mm Note 4) | Min. bending radius | 15 | 23 | 45 | 55 | 65 | 90 | 18 | 27 | 30 | 55 | 65 |
| | Bending value (Reference) | 12 | 17 | 34 | 42 | 50 | 70 | 12 | 15 | 23 | 42 | 50 |
| Operating temperature Note 2) | | –40 to +100°C, Water: 0 to +50°C (No freezing) | | | | | | | | | | |
| Material | | Nylon 12 | | | | | | | | | | |

Note 1) Refer to the "Printing/Fluid".
Note 2) Be sure to operate under the maximum operating pressure and operating temperature conditions using the lower specifications of either the tubing or fittings.
Note 3) Mount an inner sleeve when using metal One-touch fittings in high-temperature environments of 60°C or more. Use self-align fittings at a temperature of 60°C or less.
Note 4) The minimum bending radius is the representative value measured as shown in the left figure.
- Use a tube above the minimum bending radius.
- The tubing may be bent if used under the minimum bending radius. Therefore, refer to the bending value and make sure that the tubing is not bent or flattened.
- Please note that the bending value is not warranted because of the representative value when 2R is measured by the method in the left figure if the tubing is bent or flattened, etc.

## Printing/Fluid


| Print code | | Fluid |
|---|---|---|
| Previous | SMC TS 0604 SOFTNYLON 6 x 4 | Air |
| NEW | ● SMC TS 0604 SOFTNYLON 6 x 4 | Air/Water |

# ⚠ Precautions

## ⚠ Caution

1. Compatible with water due to a change in materials. Compatible fluid types are printed on the tube body for differentiation, so please be sure to check this. Note) If using the previous TS/TISA series with "water", the tube may shrink and cause air leakage or the tube may fall out.
2. The products which changed the material are applicable for general industrial water. Please contact SMC if using other kinds of fluid. Surge pressure must be under the max. operating pressure. If the surge pressure exceeds the maximum operating pressure, it will result in damage to fittings and tubes.
3. Please exercise caution when using this item in a clean room. There is a possibility of plasticizer and other materials precipitating on the tube surface and detracting from the cleanliness level of the room.

How to measure the minimum bending radius




At a temperature of 20°C, bend the tubing into a U shape. Fix one end and gradually move the other end closer. Measure 2R at the point where the outside diameter's rate of change is 10%.

## How to Order

**TS0604 W – 100**

- **TS0604**: Tubing model
- **W**: Color
- **100**: Length per roll

**Length per roll**

| Symbol | Length |
|---|---|
| 20 | 20 m roll |
| 100 | 100 m roll (Black and white only) |

**Color**

| Symbol | Color |
|---|---|
| B | Black (Translucent) |
| W | White (Material color) |
| R | Red (Translucent) |
| BU | Blue (Translucent) |
| Y | Yellow (Translucent) |
| G | Green (Translucent) |

## Made to Order

(Please contact SMC for specifications in detail, dimensions, delivery and specifications other than those mentioned above.)

| | |
|---|---|
| **100 m reel** | Metric size and Inch size except ø16: Suffix "-X3" to the end of part number. Ex.) TS0425R-100-X3 |
| **Longer length reel** | Metric size: Suffix "-X3" to the end of part number. Ex.) TS0425G-500-X3 |
| **20 m roll** | Inch size: Suffix "-X4" to the end of part number. Ex.) TISA01BU-20-X4 |

**Made to Order Availability**

| Part no. | Length \ Model | TS0425* | TS0604* | TS0806* | TS1075* | TS1209* | TISA01* | TISA05* | TISA07* | TISA11* | TISA13* | Color |
|---|---|---|---|---|---|---|---|---|---|---|---|---|
| X3 | 100 m reel | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | ○ | Black, White, Red, Blue, Yellow, Green |
| | 150 m reel | | | | ○ | | | | | | | |
| | 200 m reel | | | ○ | | | | | | | | |
| | 500 m reel | ○ | ○ | | | | | | | | | |
| X4 | 20 m roll | | | | | | ○ | ○ | ○ | ○ | ○ | Red, Blue, Yellow, Green |



SMC

# Soft Polyurethane Tubing

# Series TUS




RoHS

## Suitable for piping in confined spaces
## Extremely flexible
## Soft Polyurethane Tubing

## TUS related accessories
## Inner Sleeve
### Series TJ

Reinforces soft polyurethane tubing.
Insert an inner sleeve into soft polyurethane tubing when used with a One-touch fitting.




### Model

| Part No. | Applicable tube model | Length |
|---|---|---|
| **TJ-0425** | TUS0425 | 18 |
| **TJ-0604** | TUS0604 | 19 |
| **TJ-0805** | TUS0805 | 20.5 |
| **TJ-1065** | TUS1065 | 23 |
| **TJ-1208** | TUS1208 | 24 |

### Specifications

| | |
|---|---|
| Material | C2700T (Nickel plated) |
| Wall thickness | 0.2mm |

## ⚠ Precautions

### ⚠ Caution

①Use nylon or polyurethane tubing for general industry water to prevent the tubing from coming out or bursting due to possibility of surge pressure generation.

②The value of the max. operating pressure is at a temperature of 20°C. Refer to the burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rise which may burst the tubing.

③The value of the min. bending radius is at a temperature of 20°C. Higher temperatures allows the tubing to bend more.

④Use inner sleeve taking the removing force into consideration when used with One-touch fittings.

## Series Table


● : 20m roll ☐ : 100m roll

| Model | TUS0425 | TUS0604 | TUS0805 | TUS1065 | TUS1208 |
|---|---|---|---|---|---|
| Tube O.D. (mm) | 4 | 6 | 8 | 10 | 12 |
| Tube I.D. (mm) | 2.5 | 4 | 5 | 6.5 | 8 |
| Black (B) | ● | ● | ● | ● | ● |
| White (W) | ● | ● | ● | ● | ● |
| Red (R) | ● | ● | ● | ● | ● |
| Blue (BU) | ● | ● | ● | ● | ● |
| Yellow (Y) | ● | ● | ● | ● | ● |
| Green (G) | ● | ● | ● | ● | ● |
| Opaque (N) (1) | ● | ● | ● | ● | ● |
| Yellow brown (YB) | ● | ● | ● | ● | ● |

## Specifications

| | | | | | | |
|---|---|---|---|---|---|---|
| Fluid | | Air | | | | |
| Max. operating pressure | | 0.6MPa at 20°C | | | | |
| Burst pressure | | Refer to burst pressure characteristics curve. | | | | |
| Applicable tube fitting | | One-touch fitting, Insert tube fitting, Hose nipple (3) | | | | |
| Min. bending radius (mm) (2) | | 8 | 15 | 15 | 22 | 29 |
| Operating temperature | | –20 to +60°C (No freezing) | | | | |
| Material | | Polyurethane | | | | |
| Tube drawing strenght N (Using One-touch fitting) | Without inner sleeve | 15 | 60 | 60 | 85 | 110 |
| | With inner sleeve | 80 | 230 | 250 | 300 | 480 |


Note1) Not clear but opaque due to material.
Note2) Min. bending radius is measured as shown in the figure below.




Bend the tube into U-form at a temperature of 20°C.
Fix one end and close loop gradually. Measure 2R when the tube breaks or is crushed.

Note3) Always use inner sleeve (Series TJ) in safety circuit or critical area.

### Burst Pressure Characteristics Curve




## How to Order

TUS1065 | B | — | 100

**Indication of tube model**

**Colour indication**

| Symbol | Colour |
|---|---|
| **B** | Black |
| **W** | White |
| **R** | Red |
| **BU** | Blue |
| **Y** | Yellow |
| **G** | Green |
| **N** | Opaque |
| **YB** | Yellow brown |


**Length per roll**

| Symbol | Roll size |
|---|---|
| **20** | 20m roll |
| **100** | 100m roll (Black, Blue only) |

## Hard Polyurethane Tubing


# Series TUH

RoHS




## Maximum effective area increased nearly 44%
## TUH/Standard Type

(Compared to polyurethane tubing TU0805: O.D. 8mm, length 1m)




**Tubing inside diameter comparison** (mm)

| Tubing O.D. (øD1) | | 4 | 6 | 8 | 10 | 12 |
|---|---|---|---|---|---|---|
| Tubing I.D. (øD2) | TUH/Standard type | 2.8 | 4.4 | 5.8 | 7.3 | 8.8 |
| | TUH/High pressure type | 2.5 | 4 | 5 | 6.5 | 8 |
| | TU | | | | | |

## Operating pressure 1.0MPa (at 20°C)
## TUH/High Pressure Type

Has the same operating pressure as series TS soft nylon tubing, and a bending radius equivalent to series TU polyurethane tubing.

### Can be restored even after folding

Restoration is outstanding compared to nylon tubing, leaving no creases from folding.

# Hard Polyurethane Tubing/Standard Type

# Series TUH

RoHS




## Series

● – 20m bundle □ – 100m bundle

| Model | TUH0428 | TUH0644 | TUH0858 | TUH1073 | TUH1288 |
|---|---|---|---|---|---|
| O.D. mm | 4 | 6 | 8 | 10 | 12 |
| I.D. mm | 2.8 | 4.4 | 5.8 | 7.3 | 8.8 |
| Black (B) | ● | ● | ● | ● | ● |
| White (W) | ● | ● | ● | ● | ● |
| Blue (BU) | ● | ● | ● | ● | ● |
| Translucent (N) | ● | ● | ● | ● | ● |

## Specifications

| | | | | | |
|---|---|---|---|---|---|
| Fluid | Air Note 1) | | | | |
| Max. operating pressure (at 20°C) | 0.8MPa Note 2) | | | | |
| Min. bending radius mm | 10 | 18 | 24 | 30 | 36 |
| Burst pressure | Refer to the burst pressure characteristics curve. | | | | |
| Operating temperature | –20 to 60°C | | | | |
| Material | Polyurethane | | | | |





At a temperature of 20°C bend the tubing into a U shape. Then with one side fixed, gradually close the other side and measure 2R at the point where the tubing folds or flattens, etc.

Note 1) Consult SMC regarding other fluids.
Water cannot be used due to the occurrence of hydrolysis.

Note 2) The maximum operating pressure is the value at 20°C. Refer to the burst pressure characteristic curve for other temperatures.
Furthermore, an abnormal temperature increase due to adiabatic compression can cause tubing to burst.

Note 3) The minimum bending radius is measured at 20°C using the method shown in the figure at the left. At higher temperatures, breakage or flattening, etc., may occur at more than the minimum bending radius.

## Burst Pressure Characteristic Curve and Operating Pressure




## How to Order

**TUH0644** **B** – **20**

**Tubing model**

**Bundle length**

| Symbol | Length |
|---|---|
| **20** | 20m bundle |
| **100** | 100m bundle |

**Color**

| Symbol | Color |
|---|---|
| **B** | Black |
| **W** | White |
| **BU** | Blue |
| **N** | Translucent |

## Hard Polyurethane Tubing/High Pressure Type

# Series TUH

RoHS



### Series

● – 20m bundle □ – 100m bundle

| Model | TUH0425 | TUH0604 | TUH0805 | TUH1065 | TUH1208 |
|---|---|---|---|---|---|
| O.D. mm | 4 | 6 | 8 | 10 | 12 |
| I.D. mm | 2.5 | 4 | 5 | 6.5 | 8 |
| Black (B) | ● | ● | ● | ● | ● |
| White (W) | ● | ● | ● | ● | ● |
| Blue (BU) | ● | ● | ● | ● | ● |
| Translucent (N) | ● | ● | ● | ● | ● |


### Specifications

| | | | | | |
|---|---|---|---|---|---|
| Fluid | Air Note 1) | | | | |
| Max. operating pressure (at 20°C) | 1.0MPa Note 2) | | | | |
| Min. bending radius mm | 10 | 15 | 20 | 27 | 35 |
| Burst pressure | Refer to the burst pressure characteristics curve. | | | | |
| Operating temperature | –20 to 60°C | | | | |
| Material | Polyurethane | | | | |

Note 1) Consult SMC regarding other fluids.
Water cannot be used due to the occurrence of hydrolysis.


Note 2) The maximum operating pressure is the value at 20°C. Refer to the burst pressure characteristic curve for other temperatures.
Furthermore, an abnormal temperature increase due to adiabatic compression can cause tubing to burst.

Note 3) The minimum bending radius is measured at 20°C using the method shown in the figure at the left. At higher temperatures, breakage or flattening, etc., may occur at more than the minimum bending radius.




At a temperature of 20°C bend the tubing into a U shape. Then with one side fixed, gradually close the other side and measure 2R at the point where the tubing folds or flattens, etc.

## Burst Pressure Characteristic Curve and Operating Pressure




## How to Order

**TUH0604** **B** – **20**

**Tubing Model**

**Bundle length**

| Symbol | Length |
|---|---|
| **20** | 20m bundle |
| **100** | 100m bundle |

**Color**

| Symbol | Color |
|---|---|
| **B** | Black |
| **W** | White |
| **BU** | Blue |
| **N** | Translucent |



SMC

# *Series TUH/*Specific Product Precautions 1

**Be sure to read before handling.**

**Precautions on Usage**

## ⚠ Caution

1. Water cannot be used due to the occurance of hydrolysis.

   Use nylon or polyurethane tubing for general industrial water.

   Furthermore, consult SMC regarding use with any fluids other than air.


2. The maximum operating pressure is the value at 20°C. Refer to the burst pressure characteristic curve for other temperatures.

   Furthermore, an abnormal temperature increase due to adiabatic compression can cause tubing to burst.

3. The minimum bending radius indicates the value at which the tubing will fold at a temperature of 20°C. At higher temperatures, the tubing may fold at more than the minimum bending radius.

4. Store away from direct sunlight in a location at no more than 40°C.

# FEP Tubing (Fluoropolymer)



## Series TH

- **Heat resistance: 200°C**
  It changes according to the operating pressure.
  Refer to the graph of the max. operating pressures on page 1.

- **4 Colour variations**




- **8 Size variations**
  Metric size: ø4 to ø12

- **Applicable fittings**
  One-touch fittings (Series KQ2,KJ)
  Miniature fittings (Series M,MS) (Hose nipple type)
  Insert fittings (Series KF)
  High Purity Fluoropolymer fittings (Series LQ)

- **Applications**
  General pneumatic piping
  (Food, Semiconductor, Medical care, Automobile)

- **Certified to current Food Sanitation Legislation**
  (Ministry of Japanese Health and Safety, directive #370,1959)

# FEP Tubing (Fluoropolymer)

# *Series TH* RoHS



## Series

●-20m roll □-100m roll

| | Metric size | | | | | | | |
|---|---|---|---|---|---|---|---|---|
| Model | TH0402 | TH0425 | TH0604 | TH0806 | TH1075 | TH1008 | TH1209 | TH1210 |
| Tubing O.D. (mm) | 4 | 4 | 6 | 8 | 10 | 10 | 12 | 12 |
| Tubing I.D. (mm) | 2 | 2.5 | 4 | 6 | 7.5 | 8 | 9 | 10 |

| Colour | Symbol |
|---|---|
| Translucent | N |
| Red (Translucent) | R |
| Blue (Translucent) | BU |
| Black (Opaque) | B |

| Inch nominal size | Inch nominal size |
|---|---|
| 5/32" | 5/16" |

## Specifications

| | | | | | | | |
|---|---|---|---|---|---|---|---|
| **Fluid** Note 4) | Air, Water Note 1), Inert gas | | | | | | |
| **Applicable fittings** Note 2) | One-touch fittings: Series KQ, KJ Insert fittings: Series KF<br>Fluoropolymer fittings: Series LQ<br>Miniature fittings: Series M, MS (Hose nipple type) | | | | | | |
| **Max. operating pressure** | Refer to below "Max. Operating Pressure." | | | | | | |
| **Min. bending radius (mm)** Note 3) | 15 | 20 | 35 | 60 | 95 | 100 | 130 |
| **Operating temperature** Note 4) | Air, Inert gas: -20 to 200°C Water: 0 to 100°C (No freezing) | | | | | | |
| **Material** | FEP (Fluorinated Ethylene Propylene Resin) | | | | | | |


Note 1) When using a fluid in liquid form, the surge pressure must not exceed the maximum operating pressure. A surge pressure higher than the maximum operating pressure can cause breakage of the fittings, or rupture of the tubing. Furthermore, an abnormal temperature increase due to adiabatic compression can also result in ruptured tubing.

Note 2) Do not use in locations where the FEP tubing will move.
Be sure to operate under the maximum operating pressure conditions using the lower maximum operating specification of either the tubing or fittings.
After long term use or under high temperatures, some fittings leakage may occur due to material deterioration with age. Perform periodic inspections, and if any leakage is detected, replace with a new product immediately.
(Refer to maintenance part of "Tubing Precautions 1" on the page 7-156.)
Refer to Best Pneumatics 4 in "Fittings and Tubing" for all other precautions.
For High Purity Fluoropolymer, refer to the precautions of CAT.ES70-17, "High Purity Fluoropolymer Fittings & Tubing."

Note 3) Minimum bending radius is measured as shown left as representative values.
Allow extra length when piping since the tubing may crush if bent more than the min. bending radius.


Note 4) Consult SMC if using any other fluids.

**How to measure the minimum bending radius.**




At a temperature of 20°C, bend the tubing into a U shape. Fix one end and gradually move the other end closer. Measure 2R at the point where the outside diameter's rate of change is 5%.

## Max. Operating Pressure




Note) The maximum operating pressure varies dependant on the I.D. bore size even if the O.D. is the same.

## How to Order

**Metric size**

**TH0604** **N** — **20**

**Indication of tubing model**

**Colour indication**

| Symbol | Colour |
|---|---|
| N | Translucent |
| R | Red (Translucent) |
| BU | Blue (Translucent) |
| B | Black (Opaque) |

**Length per roll**

| Symbol | Roll size |
|---|---|
| 20 | 20m roll |
| 100 | 100m roll 1) |

1) The 100m roll is only in the colour natural as standard available

# Chemical Resistance of the Fluoropolymer FEP Material

**Chemicals in this table are inactive against FEP material Note 1), however physical properties may be effected by temperature or pressure change.**
**Please make sure that operating conditions do not cause problems since the use of FEP tubing under chemical environment is unsecured.**

| | | |
|---|---|---|
| 2-nitro-2-methyl propanol | Sodium hypochlorite | Dimethyl phthalate |
| 2-nitrobutanol | Carbon tetrachloride | Hydrofluoric acid |
| Pentabasic benzamide | Dioxane | Naphthalene fluoride |
| N-butylamine | Cyclohexanone | Nitrobenzene fluoride |
| N-octadecanol | Cyclohexane | Furan |
| N-butyl acetate | Dimethyl ether | Hexachlorethane |
| O-cresol | Dimethylsulfoxide | Hexane |
| Di-isobutyl adipate | Dimethylformamide | Ethyl hexanoate |
| Acetophenone | Bromine | Phenylcarbinol |
| Acetone | Deionized water | Benzaldehyde |
| Alniline | Nitric acid | Benzonitrile |
| Abietic acid | Mercury | Borax |
| Sulphuric chloride | Ammonium hydroxide | Boric acid |
| Isooctane | Potassium hydroxide | Formic aldehyde (Formalin) |
| Liquid ammonia | Sodium hydroxide | Acrylic anhydride |
| Ethyl alcohol | Cetane | Acetic anhydride |
| Ethyl ether | Soap, detergent | Methacrylic acid |
| Ethylene glycol | Dibutyl sebacate | Allyl methacrylate |
| Ethylenediamine | Diethyl carbonate | Vinyl methacrylate |
| Zinc chloride | Tetrachloroethylene | Methyl alcohol |
| Aluminum chloride | Tetrahydrofuran | Methyl ethyl ketone |
| Ammonium chloride | Tetrabromoethane | Methylene chloride |
| Calcium chloride | Triethanolamine | Sulphuric acid |
| Sulphuric chloride | Trichloroethylene | Phosphoric acid |
| Iron chloride (III) | Trichloroacetic acid | Iron phosphate (III) |
| Benzoyl chloride | Toluene | Tri-n-butyl phosphate |
| Magnesium chloride | Naphtha | Tricresyl phosphate |
| Hydrochloric acid | Naphthalene | |
| Chlorine (absolute) | Naphthol | |
| Aqua regia | Lead | |
| Ozone | Carbon dioxide | |
| Hydrogen peroxide | Nitrogen dioxide | |
| Natrium peroxide | Nitrobenzene | |
| Gasoline | Nitromethane | |
| Permanganate | Perchloroethylene | |
| Formic acid | Perphloroxylene | |
| Xylene | Unsymmetrical dimethylhydrazine | |
| Chromic acid | Hydrazine | |
| Chlorosulfonic acid | Pinene | |
| Chloroform | Piperidine | |
| Paraffinum liquidum | Glacial acetic acid (Acetic acid) | |
| Allyl acetate | Pyridine | |
| Ethyl acetate | Phenol | |
| Potassium | Phthalic acid | |
| Butyl acetate | Dybutyl phthalate | |

Note 1) “Inactive in chemistry terminology” means - not to cause any chemical reaction.
Reference cited: Teflon®, the fluoropolymer handbook, Manual for the chemical applications of Teflon®. Du Pond-Mitsui Fluorochemicals Co., Ltd.

Teflon® is a registered trademark for the fluoropolymer produced by E.I du Pond de Nemours & Company (Inc.) and Du Pond-Mitsui Fluorochemicals Co., Ltd.

# *Series TH*
# Tubing Precautions

**Be sure to read before handling.**

## Selection

### ⚠ Warning

#### 1. Confirm the specifications.

The products appearing in this catalogue are designed for use only in compressed air systems (including vacuum).

Do not use outside the specified ranges of pressure, temperature, etc., as this may cause damage or malfunction. (Refer to specifications.)

SMC cannot assure the product quality when fluids other than air, water and inert gas are used.

Consult with SMC for details.

#### 2. In case of using the product for medical care

This product is designed for use with compressed air system applications for medical care purposes. Do not use in contact with human bodily fluids, body tissues or transfer applications to a human living body.

### ⚠ Caution

1. Do not use in locations where the connecting threads and tubing connection will slide or rotate. The connecting theads and tubing connection will come apart under these conditions.

   Use rotary type one-touch fittings (Series KS, KX) in cases where sliding or rotation will occur. Only air can be used as the operating fluid, when using rotary type one-touch fittings.
2. Use tubing at or above the minimum bending radius. Using below the minimum bending radius can cause breakage or flattening of the tubing.
3. Never use the tubing for anything flammable, explosive or toxic such as, gas, fuel gas, or cooling mediums, since the contents can penetrate outward.

## Mounting

### ⚠ Caution

1. Before mounting confirm the model and size, etc. Also, confirm that there are no blemishes, nicks or cracks in the product.
2. When tubing is connected, consider factors such as changes in the tubing length due to pressure, and allow sufficient leeway.
3. Mount so that fittings and tubing are not subjected to twisting, pulling or moment loads. This can cause damage to fittings and flattening, bursting or disconnection of tubing, etc.
4. Mount so that tubing is not damaged due to tangling and abrasion. This can cause flattening, bursting or disconnection of tubing, etc.

## Piping

### ⚠ Caution

#### 1. Preparation before piping

Before piping is connected, it should be thoroughly blown out with air (flushing) or washed to remove chips, cutting oil and other debris from inside the pipe. Do not allow chips of the piping thread or the seal material to go in.

## Air Supply

### ⚠ Warning

#### 1. Types of fluid

This product is designed for use with compressed air. Consult SMC if a different fluid is to be used.

Consult SMC regarding products for use with general purpose fluids, to confirm which fluids can be used.

#### 2. When there is a large amount of drainage.

Compressed air containing a large amount of drainage can cause the malfunction of pneumatic equipment. An air dryer or Drain Catch should be installed upstream from filters.

#### 3. Drain management

If air filter drains are not flushed regularly, the drainage will flow downstream leading to the malfunction of pneumatic equipment.

In cases where the management of drain flushing will be difficult, the use of filters with automatic drains is recommended.

For details on the quality of compressed air mentioned above, refer to SMC's "Best Pneumatics" catalogue vol. 4.

## Operating Environment

### ⚠ Warning

1. Do not operate in locations in an explosive atmosphere.
2. Do not operate in locations where vibration or impact occurs.
3. In locations near heat resources, block off radiant heat.

## Maintenance

### ⚠ Caution

1. Check for the following during regular maintenance, and replace components as necessary.

   a) Scratches, gouges, abrasion, corrosion

   b) Leakage

   c) Twisting, flattening or distortion of tubing

   d) Hardening, deterioration or softness of tubing
2. Do not repair or patch the replaced tubing or fittings for reuse.
3. When using insert or miniature fittings over a long period, some leakage may occur due to age deterioration of the materials. Perform periodic inspections, and if any leakage is detected, correct the problem by additional tightening. If tightening becomes ineffective, replace the fittings with a new product immediately.

# Polyurethane Coil Tubing

# Series TCU



RoHS


**For flexible tubing**
**Compact piping possible**

## Specifications


| Model | TCU 0425B-1 | TCU 0425B-2 | TCU 0425B-3 | TCU 0604B-1 | TCU 0604B-2 | TCU 0604B-3 | TCU 0805B-1 |
|---|---|---|---|---|---|---|---|
| Number of tubes | 1 | 2 | 3 | 1 | 2 | 3 | 1 |
| Tube O.D. (mm) | 4 | | | 6 | | | 8 |
| Tube I.D. (mm) | 2.5 | | | 4 | | | 5 |
| Fluid | Air (1) | | | | | | |
| Max. operating pressure (2) | 0.8MPa at 20°C | | | | | | |
| Burst prssure | Refer to pressure characteristics curve. | | | | | | |
| Operating temperature | –20 to +60°C | | | | | | |
| Material | Polyurethane | | | | | | |
| Colour | Black | | | | | | |

Note 1) Consult SMC if using for other fluids than air.
Note 2) Refer to burst pressure characteristics curve for other temperatures.
Avoid abnormal temperature rises.

## Burst Pressure Characteristics Curve




## Dimensions





| Part No. \ Spec. | Tube size (mm) O.D. | Tube size (mm) I.D. | Dimension of coil (mm) L | Dimension of coil (mm) øD | No. of tubes | No. coil windings per tube length | Max. operating length (m) | Standard unit of packing |
|---|---|---|---|---|---|---|---|---|
| TCU0425B-1 | 4 | 2.5 | 210 | 18 | 1 | 52 | 1.5 | 5 tubes/ case |
| TCU0425B-2 | | | 280 | 28 | 2 | 35 | | |
| TCU0425B-3 | | | 265 | | 3 | 22 | 1 | |
| TCU0604B-1 | 6 | 4 | 325 | 24 | 1 | 54 | 2 | |
| TCU0604B-2 | | | | 37 | 2 | 27 | 1.5 | |
| TCU0604B-3 | | | 305 | | 3 | 17 | 1 | |
| TCU0805B-1 | 8 | 5 | 330 | 31 | 1 | 41 | 2 | |

∗ Dimensions are changeable due to material.

## Made to Order

(Consult SMC for detailed specifications, dimensions and delivery.)

**Change of coil turns, Color change**




| Part No. \ Spec. | Tube size (mm) O.D. | Tube size (mm) I.D. | Coil (mm) L | Coil (mm) øD | No. of tubes | No. coil windings per tube length | Max. operating length (mm) |
|---|---|---|---|---|---|---|---|
| TCU0425□-1-[N]-X6 | 4 | 2.5 | N X 4 | 18 | 1 | 3 to 90 | L X 5.9 + 200 |
| TCU0425□-2-[N]-X6 | | | N X 8 | 28 | 2 | 3 to 90 | L X 4.4 + 200 |
| TCU0425□-3-[N]-X6 | | | N X 12 | 28 | 3 | 3 to 63 | L X 2.9 + 200 |
| TCU0604□-1-[N]-X6 | 6 | 4 | N X 6 | 24 | 1 | 3 to 90 | L X 5.3 + 200 |
| TCU0604□-2-[N]-X6 | | | N X 12 | 37 | 2 | 3 to 66 | L X 3.8 + 200 |
| TCU0604□-3-[N]-X6 | | | N X 18 | 37 | 3 | 3 to 44 | L X 2.5 + 200 |

| Part No. \ Spec. | Tube size (mm) O.D. | Tube size (mm) I.D. | Coil (mm) L | Coil (mm) øD | No. of tubes | No. coil windings per tube length | Max. operating length (mm) |
|---|---|---|---|---|---|---|---|
| TCU0805□-1-[N]-X6 | 8 | 5 | N X 8 | 31 | 1 | 3 to 90 | L X 5.2 + 200 |
| TCU0805□-2-[N]-X6 | | | N X 16 | 42 | 2 | 3 to 40 | L X 3 + 200 |
| TCU1065□-1-[N]-X6 | 10 | 6.5 | N X 10 | 52 | 1 | 3 to 45 | L X 5 + 200 |
| TCU1065□-2-[N]-X6 | | | N X 20 | 52 | 2 | 3 to 35 | L X 3 + 200 |
| TCU1208□-1-[N]-X6 | 12 | 8 | N X 12 | 67 | 1 | 3 to 35 | L X 5 + 200 |
| TCU1208□-2-[N]-X6 | | | N X 24 | 67 | 2 | 3 to 30 | L X 3 + 200 |

□ → B (Black), W (White), R (Red), BU (Blue), Y (Yellow), G (Green), C (Clear), YR (Orange)
[N] → Coil turns

# Polyurethane Flat Tubing


# Series TFU



RoHS

## Compact piping possible

### Burst Pressure Characteristics Curve




## Specifications

| Part No. | TFU 0425B-2 | TFU 0425B-3 | TFU 0604B-2 | TFU 0604B-3 | TFU 0805B-2 | TFU 0805B-3 |
|---|---|---|---|---|---|---|
| Number of tubes | 2 | 3 | 2 | 3 | 2 | 3 |
| Tube O.D. (mm) | 4 | | 6 | | 8 | |
| Tube I.D. (mm) | 2.5 | | 4 | | 5 | |
| Fluid | Air (1) | | | | | |
| Max. operating pressure (2) | 0.8MPa at 20°C | | | | | |
| Burst prssure | Refer to burst pressure characteristics curve | | | | | |
| Operating temprature | –20 to +60°C (No freezing) | | | | | |
| Material | Polyurethane | | | | | |
| Colour | Black | | | | | |
| Min. bending radius (mm) | 10 | | 15 | | 20 | |
| Tube length per roll (m) | 10 | | | | | |

Note1) Consult SMC if using for other fluids than air.
Note2) Refer to burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises.

## How to Order

TFU0425 B — 2

**Indication of tube model**

**Colour indication**

| Symbol | Colour |
|---|---|
| B | Black |

**Number of tubes**


| Symbol | Number |
|---|---|
| 2 | 2 |
| 3 | 3 |

## Made to Order

(Consult SMC for detailed specifications, dimensions and delivery.)

●: 10m roll △: 50m roll □: 100m roll

| Model | TFU0425□ | TFU0604□ | TFU0805□ | TFU1065□ | TFU1208□ |
|---|---|---|---|---|---|
| Tube O.D. (mm) | 4 | 6 | 8 | 10 | 12 |
| Tube I.D. (mm) | 2.5 | 4 | 5 | 6.5 | 8 |




**① Colour change (10m roll)**

Suffix "X4" to the end of part number.
Ex.) TFU0604BU-2-10-X4
● W: White, R: Red, BU: Blue, Y: Yellow, G: Green, C: Clear, YR: Orange (All tubes are same colour.)

**② Longer roll length (50m or 100m roll)**

Suffix "X3" to the end of part number.
Ex.) TFU0425B-2-50-X3

**③ Number of tubes (10m roll)**

Suffix "X4" to the end of part number.
Ex.) TFU0604B-4-10-X4

Flame Resistance (Equivalent to UL-94 Standard V-0)

# FR Soft Nylon Tubing


# Series TRS



RoHS

**Applicable for general air pressure and water in a spark atomosphere such as spot welding.**
**Flame resistance tube**

## Burst Pressure Characteristics Curve




## Series Table

● : 20m roll □ : 100m roll

| Model | TRS0603 | TRS0805 | TRS1065 | TRS1208 |
|---|---|---|---|---|
| Tube O.D. (mm) | 6 | 8 | 10 | 12 |
| Tube I.D. (mm) | 3 | 5 | 6.5 | 8 |
| Black (B) | ● | ● | ● | ● |
| White (W) | ● | ● | ● | ● |
| Red (R) | ● | ● | ● | ● |
| Blue (BU) | ● | ● | ● | ● |
| Green (G) | ● | ● | ● | ● |

## Specifications

| | | | | |
|---|---|---|---|---|
| Fluid | Air, Water | | | |
| Max. operating pressure | 1.2MPa at 20°C | | | |
| Burst pressure | Refer to burst pressure characteristics curve. | | | |
| Min. bending radius (mm) | 17 | 19 | 27 | 32 |
| Operating temperature | –20 to +60°C (Water: 0 to 60°C)(No freezing) | | | |
| Material | Flame resistance nylon (UL-94 Standard V-0) | | | |

## ⚠ Precautions

### ⚠ Caution

①Applicable for general industry water. Consult SMC if using for other kinds of fluid. Surge pressure must be under the max. operating pressure. If exceeding that value, fitting may be damaged and tubing may be burst.

②The value of the max. operating pressure is at a temperature of 20°C. Refer to the burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises which may burst the tubing.

③The value of the min. bending radius is at a temperature of 20°C and O.D. variable rate 10% max. In case that operating temperature is higher than 20°C, O.D. variable rate may be over 10% even if bending radius is within the specified range.

## How to Order

TRS1065 | B | 100

**Indication of tube model**

**Length per roll**

| Symbol | Roll size |
|---|---|
| **20** | 20m roll |
| **100** | 100m roll |

**Colour indication**

| Symbol | Colour |
|---|---|
| **B** | Black |
| **W** | White |
| **R** | Red |
| **BU** | Blue |
| **G** | Green |

## Flame Resistance (Equivalent to UL-94 Standard V-0)


# FR Double Layer Tubing

# *Series TRB*

RoHS

**Suitable for air and water piping in environments where sparks from spot welders, etc., may be a problem.**
**Double layer design using flame resistant resin (equivalent to UL-94 Standard V-0) for outer layer.**





FR double layer tubing
(sectional view)

## Series Table

●: 20m roll □: 100m roll


| Model | | TRB0604 | TRB0806 | TRB1075 | TRB1209 |
|---|---|---|---|---|---|
| Inner tube O.D. (mm) | | 6 | 8 | 10 | 12 |
| Inner tube I.D. (mm) | | 4 | 6 | 7.5 | 9 |
| Outer layer thickness (mm) | | 1 | 1 | 1 | 1 |
| Outer layer colour (1) | Black (B) | ● | ● | ● | ● |
| | White (W) | ● | ● | ● | ● |
| | Red (R) | ● | ● | ● | ● |
| | Blue (BU) | ● | ● | ● | ● |
| | Yellow (Y) | ● | ● | ● | ● |
| | Green (G) | ● | ● | ● | ● |
| Minimum bending radius (mm) (4) | | 15 | 28 | 35 | 45 |

## Specifications

| | | |
|---|---|---|
| Fluid | | Air, Water (2) |
| Max. operating pressure (3) | | 1.0MPa at 20°C |
| Burst pressure | | Refer to burst pressure characteristics curve. |
| Ambient and fluid temperature | | –20 to +60°C (Water: 0 to 60°C) (No freezing) |
| Material | Inner tube | Nylon 12 |
| | Outer layer | PVC (Equivalent to UL-94 Standard V-0) |

Note1) The colour of all inner tube is black.
Note2) Applicable for general industry water. Consult SMC if using for other kinds of fluid. Surge pressure must be under the max. operating pressure.
Note3) Refer to burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises.
Note4) The value for a temperature of 20°C and O.D.variable rate 10% max.

## Burst Pressure Characteristics Curve




## How to Order

TRB1075 | B | — | 100

**Indication of tube model**

**Colour indication**

| Symbol | Colour | Symbol | Colour |
|---|---|---|---|
| **B** | Black | **BU** | Blue |
| **W** | White | **Y** | Yellow |
| **R** | Red | **G** | Green |


**Length per roll**

| Symbol | Roll size |
|---|---|
| **20** | 20m roll |
| **100** | 100m roll |

## How to Install to One-touch Fitting

### ⚠ Caution

Length of tube to be inserted into One-touch fitting is indicated on the outer layer of TRB tubing.
Cut the tube according to this indication. (Procedure①) and then strip off the outer layer. (Procedure②) for installing tube.




# ⚠ Precautions

### ⚠ Caution

①Applicable for general industrial water. Consult SMC if using for other kinds of fluid. Surge pressure must be under the max. operating pressure. If exceeding that value, fitting may be damaged and tubing may be burst.

②The value of the max. operating pressure is at a temperature of 20°C. Refer to the burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises which may burst the tubing.


③The value of the min. bending radius is at a temperature of 20°C and O.D. variable rate 10% max. In case that operating temperature is higher than 20°C, O.D. variable rate may be over 10% even if bending radius is within the specified range.

# Flame Resistant (Equivalent to UL-94 Standard V-0) FR Double Layer Polyurethane tubing

# Series TRBU

RoHS






Sectional view of FR double layer tube

## Series Table

● - 20m bundle □ - 100m reel


| Model | TRBU0604 | TRBU0805 | TRBU1065 | TRBU1208 |
|---|---|---|---|---|
| Internal tube O.D. mm | 6 | 8 | 10 | 12 |
| Internal tube I.D. mm | 4 | 5 | 6.5 | 8 |
| External layer thickness mm | 1 | 1 | 1 | 1 |
| External layer colour Note 1) Black (B) | ● | ● | ● | ● |
| White (W) | ● | ● | ● | ● |
| Red (R) | ● | ● | ● | ● |
| Blue (BU) | ● | ● | ● | ● |
| Yellow (Y) | ● | ● | ● | ● |
| Green (G) | ● | ● | ● | ● |
| Minimum bend radius mm Note 4) | 15 | 20 | 27 | 35 |

## Specifications

| Fluid | | Air, Water Note 2) |
|---|---|---|
| Maximum operating pressure (at 20°C) Note 3) | | 0.8MPa {8.2kgf/cm²} |
| Burst pressure | | Refer to burst pressure characteristics curve |
| Ambient and fluid temperature | | –20 to 60°C<br>For water 0 to 40°C (without freezing) |
| Materials | Internal tube | Polyurethane |
| | External layer | PVC (equivalent to UL-94 standard V-0) |

Note 1) The colour of all internal tubes is black.
Note 2) Can be used with general industrial water. Contact SMC if used with other fluids. Also keep surge pressure at or below the maximum operating pressure.
Note 3) In case of other temperatures, refer to the burst pressure characteristics curve. In addition, operate so that abnormal temperature rise due to adiabatic compression does not occur.
Note 4) Indicates the bending value of the tubing at a temperature of 20°C.

## Burst Pressure Characteristics Curve and Operating Pressure




## How to Order

**TRBU1065 B — 100**

- **Tube model**
- **Colour**

| Symbol | Colour | Symbol | Colour |
|---|---|---|---|
| **B** | Black | **BU** | Blue |
| **W** | White | **Y** | Yellow |
| **R** | Red | **G** | Green |


- **Roll length**

| Symbol | Length |
|---|---|
| **20** | 20m bundle |
| **100** | 100m reel |

## Installation on One-touch Fittings

### ⚠ Caution

Since the pitch length for installation on a One-touch fitting is indicated on the external layer of TRBU tubing, cut the tubing according to this indication (Step 1), strip off the external layer only (Step 2), and then install on the One-touch fitting.




**Precautions on Useage**

### ⚠ Caution

1. Useage is possible with general industrial water. Contact SMC if product will be used with other fluids. Also, keep surge pressure at or below the maximum operating pressure. If surge pressure exceeds the maximum operating pressure, this can cause damage to fittings or bursting of the tubing.
2. The maximum operating pressure is the value when at 20°C. In case of other temperatures, refer to the burst pressure characteristics curve. Furthermore, bursting of the tubing can be caused by an abnormal temperature rise due to adiabatic compression.
3. The minimum bend radius indicates the bending value of the tubing at a temperature of 20°C. The tubing may bend beyond the minimum bend radius at higher temperatures.
4. Tubing should be stored in a location out of direct sunlight and at 40°C or below.

# Antistatic Tubing

# Series TA□ RoHS

## Conductive tubing prevents troubles caused by static electricity.


## Antistatic soft nylon tubing/Series TAS

**For air pressure piping to product or assembly while preventing static electricity.**

**Flame resistant tube (UL-standard, V-0)**



### Burst Pressure Characteristics Curve




### Series Table

●: 20m roll □: 100m roll

| Model | TAS3222 | TAS0425 | TAS0604 | TAS0805 | TAS1065 | TAS1208 |
|---|---|---|---|---|---|---|
| Tube O.D. (mm) | 3.2 | 4 | 6 | 8 | 10 | 12 |
| Tube I.D. (mm) | 2.2 | 2.5 | 4 | 5 | 6.5 | 8 |
| Black (B) | ● | ● | ● | ● | ● | ● |

### Specifications

| | | | | | | |
|---|---|---|---|---|---|---|
| Max. operating pressure(1) | 1.2MPa at 20°C | | | | | |
| Burst pressure | Refer to burst pressure characteristics curve. | | | | | |
| Min. bending radius (mm)(2) | 12 | 12 | 15 | 19 | 27 | 32 |
| Operating temperature | 0 to 40°C | | | | | |
| Material | Conductive nylon + Flame resistant nylon (UL-94standard, V-0) | | | | | |
| Surface resistance | $10^4$ to $10^7\,\Omega$ | | | | | |

Note1) Refer to burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises.
Note2) The value at temperature of 20°C and O.D. variable rate 10% max.

### How to Order

**TAS1065 B — 100**

- TAS1065: Indication of tube model
- B: Colour indication

| Symbol | Colour |
|---|---|
| B | Black |

- 100: Length per roll

| Symbol | Roll size |
|---|---|
| 20 | 20m roll |
| 100 | 100m roll |


## Antistatic polyurethane tubing/Series TAU

**For air pressure piping to product or assembly while preventing static electricity.**

**Flexible tube**



### Burst Pressure Characteristics Curve




### Series Table

●: 20m roll □: 100m roll

| Model | TAU3220 | TAU0425 | TAU0604 | TAU0805 | TAU1065 | TAU1208 |
|---|---|---|---|---|---|---|
| Tube O.D. (mm) | 3.2 | 4 | 6 | 8 | 10 | 12 |
| Tube I.D. (mm) | 2 | 2.5 | 4 | 5 | 6.5 | 8 |
| Black (B) | ● | ● | ● | ● | ● | ● |

### Specifications

| | | | | | | |
|---|---|---|---|---|---|---|
| Max. operating pressure(1) | 0.9MPa at 20°C | | | | | |
| Burst pressure | Refer to burst pressure characteristics curve. | | | | | |
| Min. bending radius (mm)(2) | 10 | 10 | 15 | 20 | 27 | 35 |
| Operating temperature | 0 to 40°C | | | | | |
| Material | Conductive polyurethane | | | | | |
| Surface resistance | $10^4$ to $10^7\,\Omega$ | | | | | |

Note1) Refer to burst pressure characteristics curve for other temperatures. Avoid abnormal temperature rises.
Note2) The value at temperature of 20°C.

### How to Order

**TAU1065 B — 100**

- TAU1065: Indication of tube model
- B: Colour indication

| Symbol | Colour |
|---|---|
| B | Black |

- 100: Length per roll

| Symbol | Roll size |
|---|---|
| 20 | 20m roll |
| 100 | 100m roll |