PSA 信昌電子陶瓷股份有限公司

Prosperity Dielectrics Co., Ltd.

No.566-1, Kaoshi Rd., Yangmei, Taoyuan 32668, Taiwan (R.O.C.)

Tel : 886-3-4753355 Fax : 886-3-4854959

Messrs. : 一般共用

Date : 2018/08/17

APPROVAL SHEET

Product Name : Medium Voltage Multilayer Ceramic Chip Capacitors

Part No. : FM Series

Description : Size 0402~2225, C0G/X7R/Y5V, 100Vdc~630Vdc

PREPARED BY	APPROVED BY

信昌電子陶瓷股份有限公司

PROSPERITY DIELECTRICS CO., LTD.

桃園市楊梅區高獅路 566-1 號 http://www.pdc.com.tw

Tel : 03-4753355 ext : **Fax : 03-4854959**

Contactor : _____ **Mobile :** _____

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved.

PSA 信昌電子陶瓷股份有限公司

Prosperity Dielectrics Co., Ltd.

No.566-1, Kaoshi Rd., Yangmei, Taoyuan 32668, Taiwan (R.O.C.)

Tel : 886-3-4753355 Fax : 886-3-4854959

SPECIFICATION

FOR

Product Name : Medium Voltage Multilayer Ceramic Chip Capacitors

Part No. : FM Series

Description : Size 0402~2225, C0G/X7R/Y5V, 100Vdc~630Vdc

著作權所有 侵害必究 信昌電子陶瓷股份有限公司 PSA Prosperity Dielectrics Co., LTD. COPYRIGHT © PROSPERITY DIELECTRICS CO., LTD. ALL RIGHTS RESERVED

SPEC. No. : FM-000-001-13
DATE : 2018/08/17

DRAWN BY	CHECEKED BY	APPROVED BY
Tsu Chen	Yvens Chou	Joseph Ling

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved.

PSA 信昌電子陶瓷股份有限公司

Prosperity Dielectrics Co., Ltd.

1. INTRODUCTION

FM Series green type capacitors are manufactured by using green materials without lead and cadmium. These capacitors feature series connection of multi-layer capacitor units in a MLCC to realize high voltage performance. Reliable performances are built-in through exact formulation of dielectric powders, preparation of conductive paste, advanced automatic manufacturing, and strict quality control to assure excellent control in dielectric thickness, electrode integrity, and electrode-to-termination continuity.

2. FEATURES

a. Medium voltage in a given case size.
b. High reliability and stability.
c. RoHS compliant.

3. APPLICATIONS

a. DC to DC converter.
b. High voltage coupling/DC blocking.
c. Back-lighting inverters.
d. Snubbers in high frequency power converters.

4. HOW TO ORDER

FM	31	X	471	K	251	P	X	G
PDC Family	Size	Dielectric	Capacitance	Tolerance	Rated Voltage	Packaging	Thickness	Control Code
Table 1	Table 2	Table 3	Table 4	Table 5	Table 6	Table 7	Table 8	Table 9

Table 1 PDC Family

Code	Description
FM	100V≤Rated Voltage≤630V series

Table 2 Size

Code	Description	Code	Description	Code	Description
15	0402 (1005)	32	1210 (3225)	52	2211 (5728)
18	0603 (1608)	42	1808 (4520)	55	2220 (5750)
21	0805 (2012)	43	1812 (4532)	56	2225 (5763)
31	1206 (3216)	46	1825 (4563)		

Table 3 Dielectric Material Characteristics

Code	Description	Code	Description
N	C0G	X	X7R
F	Y5V		

Table 4 Capacitance Rule Code

Code	Description	Code	Description
R47	0.47pF	102	102=10x10^2=1000pF
0R5	0.5pF	104	104=10x10^4=100nF
100	100=10x10^0=10pF	106	106=10x10^6=10μF

Table 5 Tolerance

Code	Description	Code	Description	Code	Description
A	±0.05 pF	J	±5 %	X	+10%~+20%
B	±0.10 pF	K	±10 %		
C	±0.25 pF	L	0% ~ +10%		
D	±0.50 pF	M	±20 %		
F	±1 %	N	-5% ~ +10%		
G	±2 %	P	±0.02 pF		
H	±3 %	Q	±0.03 pF		
I	-10% ~ 0%	Z	-20% ~ +80%		

Table 6 Rated Voltage

Code	Description	Code	Description	Code	Description
101	100Vdc	251	250Vdc	501	500Vdc
201	200Vdc	401	400Vdc	631	630Vdc

Table 7 Packaging Type

Code	Description	Code	Description
B	Bulk	T	Tray package
E	Tape and 7" Reel, Embossed Tape	P	Tape and 7" Reel, Paper Tape
K	Tape and 10" Reel, Embossed Tape	D	Tape and 10" Reel, Paper Tape
L	Tape and 13" Reel, Embossed Tape	G	Tape and 13" Reel, Paper Tape

Table 8 Thickness Description

Code	Description	Code	Description	Code	Description
A	0.60 ± 0.10 mm	I	1.25 ± 0.20 mm	Q	0.50 +0.02/-0.05 mm
B	0.8 + 0.15/-0.10 mm	J	1.15 ± 0.15 mm	R	3.10 ± 0.30 mm
C	1.25 ± 0.10 mm	K	0.50 ± 0.20 mm	S	0.80 ± 0.07 mm
D	1.40 ± 0.15 mm	L	0.30 ± 0.03 mm	T	0.85 ± 0.10 mm
E	1.60 ± 0.20 mm	M	0.95 ± 0.10 mm	U	0.50 ± 0.10 mm
F	2.00 ± 0.20 mm	N	0.50 ± 0.05 mm	V	0.20 ± 0.02 mm
G	2.50 ± 0.30 mm	O	3.50 ± 0.20 mm	X	0.80 ± 0.10 mm
H	2.80 ± 0.30 mm	P	1.60 +0.3/-0.10 mm	Z	0.25 ± 0.03 mm

Table 9 Special Control Code

Code	Description
G	RoHS Compliant
Q	Surface Coating (Size 1206~2225)
O	Gold plating (Size≥0603)

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2

5. EXTERNAL DIMENSIONS

Size Inch (mm)	L (mm)	W (mm)	Code / T (mm)	M_B (mm)
0402(1005)	1.00±0.10	0.50±0.10	See No.4 Reference Table 8	0.25 +0.05/-0.10
0603(1608)	1.60±0.15	0.80±0.15		0.40±0.15
0805(2012)	2.00±0.20	1.25±0.20		0.50±0.20
1206(3216)	3.20±0.20 3.20 +0.30/-0.10#	1.60±0.20 1.60 +0.30/-0.10#		0.60±0.20
1210(3225)	3.20±0.30	2.50±0.30		0.75±0.35
1808(4520)	4.50±0.40	2.00±0.25		0.75±0.35
1812(4532)	4.50±0.40	3.20±0.30		0.75±0.35
1825(4563)	4.50±0.40	6.30±0.40		0.75±0.35
2220(5750)	5.70±0.40	5.00±0.40		0.85±0.35
2225(5763)	5.70±0.40	6.30±0.40		0.85±0.35




Fig. 5.1 The outline of MLCC

"#"For 1206 size P thickness products.

6. GENERAL ELECTRICAL DATA

Dielectric	C0G	X7R	Y5V
Size	0402, 0603, 0805, 1206, 1210, 1808, 1812, 1825, 2220, 2225	0402, 0603, 0805, 1206, 1210, 1808, 1812, 1825, 2220, 2225	0805, 1206, 1210, 1812
Rated voltage (WVDC)	100V, 200V, 250V, 500V, 630V	100V, 200V, 250V, 500V, 630V	100V, 200V, 250V
Capacitance range	0.5pF ~ 100nF	100pF ~ 820nF	10nF to 680nF
Capacitance tolerance	Reference to Table5	Reference to Table5	Reference to Table5
Tan δ	Cap. Rang / Q Spec. Cap.<30pF: Q≥400+20C Cap.≥30pF: Q≥1000	≤2.5% ~ ≤10.0%	≤5.0%
Capacitance & Tan δ Test condition	Measured at the condition of 30~70% related humidity		
	For 25°C at ambient temperature	Preconditioning for Class II MLCC : Perform a heat treatment at 150±10°C for 1 hour, then leave in ambient condition for 24±2 hours before measurement	
	Cap. Rang / Test Condition Cap.≤1000pF: 1.0±0.2Vrms, 1.0MHz±10% Cap.>1000pF: 1.0±0.2Vrms, 1.0KHz±10%	1.0±0.2Vrms, 1.0KHz±10%, at 25°C ambient temperature	1.0±0.2Vrms, 1.0KHz±10%, at 20°C ambient temperature
Insulation resistance at Ur	≥10GΩ or RxC≥500Ω-F, whichever is smaller	≥10GΩ or RxC≥100Ω-F, whichever is smaller	
Operating temperature	-55 to +125°C		-25 to +85°C
Capacitance characteristic	±30ppm/°C	±15%	+30/-80%
Termination	Cu or Ag/Ni/Sn or Au (lead-free termination)		

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2

7. CAPACITANCE RANGE

7-1. C0G

Dimension		0402			0603			0805					1206				
Cap(pF)	code	100V	200V	250V	100V	200V	250V	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V
0.5	0R5	N	N	N	S	S	S	A	A	A	A	A					
1.0	1R0	N	N	N	S	S	S	A	A	A	A	A					
1.2	1R2	N	N	N	S	S	S	A	A	A	A	A	X			X	
1.5	1R5	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
1.8	1R8	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
2.2	2R2	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
2.7	2R7	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
3.3	3R3	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
3.9	3R9	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
4.7	4R7	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
5.6	5R6	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
6.8	6R8	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
8.2	8R2	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
10	100	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
12	120	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
15	150	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
18	180	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
22	220	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
27	270	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
33	330	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
39	390	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
47	470	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
56	560	N	N	N	S	S	S	A	A	A	A	A	X	X	X	X	X
68	680	N	N		S	S	S	A	A	A	A	A	X	X	X	X	X
82	820	N	N		S	S	S	A	A	A	X	X	X	X	X	X	X
100	101	N	N		S	S	S	A	A	X	X	X	X	X	X	X	X
120	121	N			S	S	S	A	A	X	C	C	X	X	X	X	X
150	151	N			S	S	S	A	X	X	C	C	X	X	X	X	X
180	181	N			S	S	S	A	X	C	C	C	X	X	X	X	X
220	221	N			S	S	S	A	C	C	C	C	X	X	X	X	X
270	271				S	B	B	A	C	C	C	C	X	X	M	M	M
330	331				S	B	B	A	C	C	C	C	X	X	M	M	M
390	391				S	B	B	X	C	C	C	C	X	X	M	M	M
470	471				S	B	B	X	C	C	I	I	X	M	M	M	M
560	561				S	B	B	X	C	C	I	I	X	M	C	C	C
680	681				S			X	C	C	I	I	X	M	C	C	C
820	821				S			X	C	C	I	I	X	M	E	E	E
1000	102				S			X	C	C	I	I	X	M	E	E	E
1200	122				B			X	C	C			X	M	E	E	E
1500	152				B			X	C	C			X	C	E	E	E
1800	182							X	C	C			X	C	E	E	E
2200	222							X	C	C			M	C	E	E	E
2700	272							C	C	C			M	C	E	E	E
3300	332							C					C	C	E	E	E
3900	392							C					C	E	E	E	E
4700	472							C					C	E	E	E	E
5600	562							C					E	E	E	E	
6800	682							C					E	E	E	E	
8200	822												E	E	E		
10000	103												E	E	E		
12000	123												P				
15000	153												P				
18000	183												P				
22000	223												P				
27000	273																
33000	333																

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2

7. CAPACITANCE RANGE

7-1. C0G

Dimension		1210					1808					1812				
Cap(pF)	code	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V
2.2	2R2						C	C	C	C	C					
2.7	2R7						C	C	C	C	C					
3.3	3R3						C	C	C	C	C					
3.9	3R9						C	C	C	C	C					
4.7	4R7						C	C	C	C	C					
5.6	5R6						C	C	C	C	C					
6.8	6R8						C	C	C	C	C					
8.2	8R2						C	C	C	C	C					
10	100	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
12	120	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
15	150	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
18	180	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
22	220	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
27	270	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
33	330	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
39	390	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
47	470	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
56	560	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
68	680	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
82	820	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
100	101	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
120	121	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
150	151	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
180	181	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
220	221	M	M	M	M	M	C	C	C	C	C	C	C	C	C	C
270	271	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
330	331	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
390	391	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
470	471	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
560	561	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
680	681	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
820	821	M	M	M	M	M	C	C	C	F	F	C	C	C	C	C
1000	102	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
1200	122	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
1500	152	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
1800	182	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
2200	222	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
2700	272	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
3300	332	M	C	C	C	C	C	C	C	F	F	C	C	C	C	C
3900	392	M	C	C	C	C	C	C	C			C	C	C	C	C
4700	472	M	E	E	C	C	C	C	C			C	C	C	C	C
5600	562	C	E	E	C	C	C	E	E			C	C	C	C	C
6800	682	C	E	E	E	E	C	E	E			C	C	C	C	C
8200	822	C	E	E	E	E	E	F	F			C	C	C	C	C
10000	103	E	F	F	F	F	E	F	F			C	C	C	C	C
12000	123	E	F									C	E	E	E	E
15000	153	F	G									C	E	E	E	E
18000	183	G	G									E	F	F	F	F
22000	223	G	G									E	F	F	F	F
27000	273	G										F	G	G		
33000	333	G										F				
39000	393	G										G				
47000	473	G										G				
56000	563											G				
68000	683											G				
82000	823											G				
100000	104											G				

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2

7. CAPACITANCE RANGE

7-1. C0G

Dimension		1825					2220					2225				
Cap(pF)	code	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V
10	100	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
12	120	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
15	150	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
18	180	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
22	220	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
27	270	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
33	330	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
39	390	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
47	470	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
56	560	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
68	680	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
82	820	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
100	101	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
120	121	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
150	151	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
180	181	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
220	221	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
270	271	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
330	331	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
390	391	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
470	471	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
560	561	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
680	681	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
820	821	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
1000	102	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
1200	122	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
1500	152	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
1800	182	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
2200	222	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
2700	272	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
3300	332	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
3900	392	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
4700	472	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
5600	562	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
6800	682	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
8200	822	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
10000	103	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
12000	123	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
15000	153	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
18000	183	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
22000	223	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
27000	273	F	F	F	F		F	F	F	F		F	F	F	F	F
33000	333	F	F	F	F		F	F	F	F		F	F	F	F	F
39000	393	F	F	F	F		F	F	F	G		F	F	F	F	F
47000	473	F	F	F	F		F	G	G	G		F	F	F	F	F
56000	563	F	G	G			F	G	G			F	G	G	G	G
68000	683	F	G	G			F	G	G			F	G	G	G	G
82000	823	G					G					F	G	G	G	
100000	104	G					G					G	G	G		
120000	124															
150000	154															
180000	184															
220000	224															

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2

7. CAPACITANCE RANGE

7-2. X7R

Dimension		0402	0603			0805					1206				
Cap(pF)	code	100V	100V	200V	250V	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V
100	101	N	S	B	B	X	X	X	X	X	X	C	C	C	C
120	121	N	S	B	B	X	X	X	X	X	X	C	C	C	C
150	151	N	S	B	B	X	X	X	X	X	X	C	C	C	C
180	181	N	S	B	B	X	X	X	X	X	X	C	C	C	C
220	221	N	S	B	B	X	X	X	X	X	X	C	C	C	C
270	271	N	S	B	B	X	X	X	X	X	X	C	C	C	C
330	331	N	S	B	B	X	X	X	X	X	X	C	C	C	C
390	391	N	S	B	B	X	X	X	X	X	X	C	C	C	C
470	471	N	S	B	B	X	X	X	X	X	X	C	C	C	C
560	561	N	S	B	B	X	X	X	X	X	X	C	C	C	C
680	681	N	S	B	B	X	X	X	X	X	X	C	C	C	C
820	821	N	S	B	B	X	X	X	X	X	X	C	C	C	C
1000	102	N	S	B	B	X	X	X	X	X	X	C	C	C	C
1200	122	N	S	B	B	X	X	X	X	X	X	C	C	C	C
1500	152	N	S	B	B	X	X	X	X	X	X	C	C	C	C
1800	182	N	S	B	B	X	X	X	X	X	X	C	C	C	C
2200	222	N	S	B	B	X	X	X	X	X	X	C	C	C	C
2700	272	N	S	B	B	X	X	X	X	X	X	C	C	C	C
3300	332	N	S	B	B	X	X	X	X	X	X	C	C	C	C
3900	392	N	S	B	B	X	X	X	X	X	X	C	C	C	C
4700	472	N	S	B	B	X	X	X	C	C	X	C	C	C	C
5600	562		S	B	B	X	X	X	C	C	X	C	C	C	C
6800	682		S	B	B	X	X	X	C	C	X	C	C	C	C
8200	822		S	B	B	X	X	X	C	C	X	C	C	C	C
10000	103		S	B	B	X	C	C	C	C	X	C	C	C	C
12000	123		B			X	C	C	C	C	X	C	C	C	C
15000	153		B			X	C	C	C	C	X	C	C	C	C
18000	183		B			X	C	C	C	C	X	C	C	C	C
22000	223		B			X	C	C	C	C	X	C	C	E	E
27000	273		B			C	C	C	C	C	X	C	C	E	E
33000	333		B			C	C	C	C	C	X	E	E	E	E
39000	393		B			C	C	C			X	E	E	E	E
47000	473		B			C	C	C			X	E	E	E	E
56000	563		B			C	C	C			X	E	E	E	E
68000	683		B			C	C	C			X	E	E		
82000	823		B			C	C				C	E	E		
100000	104		B			C	C				C	E	E		
120000	124					I					C	E	E		
150000	154					I					E	E	E		
180000	184					I					E	E	E		
220000	224					I					E	E	E		
270000	274					I					E				
330000	334					I					E				
390000	394					I					E				
470000	474					I					E				
560000	564										P				
680000	684										P				
820000	824										P				

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2

7. CAPACITANCE RANGE

7-2. X7R

Dimension		1210					1808		1812				
Cap(pF)	code	100V	200V	250V	500V	630V	500V	630V	100V	200V	250V	500V	630V
100	101												
120	121												
150	151						C	C					
180	181						C	C					
220	221	M	M	M	C	C	C	C					
270	271	M	M	M	C	C	C	C	C	C	C	C	C
330	331	M	M	M	C	C	C	C	C	C	C	C	C
390	391	M	M	M	C	C	C	C	C	C	C	C	C
470	471	M	M	M	C	C	C	C	C	C	C	C	C
560	561	M	M	M	C	C	C	C	C	C	C	C	C
680	681	M	M	M	C	C	C	C	C	C	C	C	C
820	821	M	M	M	C	C	C	C	C	C	C	C	C
1000	102	M	M	M	C	C	C	C	C	C	C	C	C
1200	122	M	M	M	C	C	C	C	C	C	C	C	C
1500	152	M	M	M	C	C	C	C	C	C	C	C	C
1800	182	M	M	M	C	C	C	C	C	C	C	C	C
2200	222	M	M	M	C	C	C	C	C	C	C	C	C
2700	272	M	M	M	C	C	C	C	C	C	C	C	C
3300	332	M	M	M	C	C	C	C	C	C	C	C	C
3900	392	M	M	M	C	C	C	C	C	C	C	C	C
4700	472	M	M	M	C	C	C	C	C	C	C	C	C
5600	562	M	M	M	C	C	F	F	C	C	C	C	C
6800	682	M	M	M	C	C	F	F	C	C	C	C	C
8200	822	M	M	M	C	C	F	F	C	C	C	C	C
10000	103	M	M	M	C	C	F	F	C	C	C	C	C
12000	123	M	M	M	C	C	F	F	C	C	C	C	C
15000	153	M	M	M	C	C	F	F	C	C	C	C	C
18000	183	M	M	M	C	C	F	F	C	C	C	C	C
22000	223	M	M	M	C	C	F	F	C	C	C	C	C
27000	273	M	M	M	E	E	F	F	C	C	C	C	C
33000	333	M	M	M	E	E	F	F	C	C	C	C	C
39000	393	M	M	M	E	E	F	F	C	C	C	C	C
47000	473	M	C	C	E	E	F	F	C	C	C	C	C
56000	563	M	C	E	E	E	F	F	C	C	C	F	F
68000	683	M	E	E	F	F	F	F	C	C	C	F	F
82000	823	M	E	E	F	F	F	F	C	C	C	F	F
100000	104	M	E	E	F	F			C	C	C	F	F
120000	124	M	E	E					C	C	C	G	G
150000	154	C	G	G					C	F	F	G	G
180000	184	C	G	G					C	F	F	G	G
220000	224	C	G	G					C	F	F	G	G
270000	274	E	G	G					C	F	F	G	
330000	334	E	G	G					C	F	F	G	
390000	394	G	G	G					C	F	F	G	
470000	474	G	G	G					F	F	F	G	
560000	564	G	G	G					F	G	G		
680000	684	G	G	G					F	G	G		
820000	824	G							F	G	G		

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2

7. CAPACITANCE RANGE

7-2. X7R

Dimension		1825					2220					2225				
Cap(pF)	code	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V	100V	200V	250V	500V	630V
1000	102	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
1200	122	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
1500	152	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
1800	182	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
2200	222	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
2700	272	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
3300	332	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
3900	392	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
4700	472	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
5600	562	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
6800	682	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
8200	822	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
10000	103	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
12000	123	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
15000	153	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
18000	183	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
22000	223	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
27000	273	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
33000	333	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
39000	393	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
47000	473	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
56000	563	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
68000	683	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
82000	823	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
100000	104	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
120000	124	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
150000	154	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
180000	184	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
220000	224	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
270000	274	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
330000	334	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
390000	394	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
470000	474	F	F	F	F	F	F	F	F	F	F	F	F	F	F	F
560000	564	F	F	F	G	G	F	F	F			F	F	F	F	F
680000	684	F	F	F			F	F	F			F	F	F		
820000	824	F	F	F			F	F	F			F	F	F		

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2

7. CAPACITANCE RANGE

7-3. Y5V

Dimension		0805			1206			1210			1812		
Cap(μF)	code	100V	200V	250V	100V	200V	250V	100V	200V	250V	100V	200V	250V
0.010	103	B	B	B	B	B	B	C	C	C	D	D	D
0.015	153	B	B	B	B	B	B	C	C	C	D	D	D
0.022	223	B	B	B	B	B	B	C	C	C	D	D	D
0.033	333	B	B	B	B	B	B	C	C	C	D	D	D
0.047	473	B	B	B	B	B	B	C	C	C	D	D	D
0.068	683	B	B	B	B	B	B	C	C	C	D	D	D
0.10	104	B			B	B	B	C	C	C	D	D	D
0.15	154				C	C	C	C	C	C	D	D	D
0.22	224				C			C			D	D	D
0.33	334							C			D	D	D
0.47	474										D	D	D
0.68	684										D	D	D

著作權所有 侵害必究
信昌電子陶瓷股份有限公司
PSA
PASSIVE SYSTEM ALLIANCE
Prosperity Dielectrics Co., Ltd.
COPYRIGHT © PROSPERITY DIELECTRICS CO., LTD. ALL RIGHTS RESERVED.

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved.

8. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

<table>
<tr><th>No.</th><th>Item</th><th>Test Condition</th><th>Requirements</th></tr>
<tr><td>1.</td><td>Visual and Dimensions</td><td>---</td><td>* No remarkable defect.
* Dimensions to confirm to individual specification sheet.</td></tr>
<tr><td>2.</td><td>Capacitance</td><td rowspan="2">* Class I : C0G
Cap.≤1000pF, 1.0±0.2Vrms, 1MHz±10%.
Cap.>1000pF, 1.0±0.2Vrms, 1KHz±10%.
* Class II : (X7R, Y5V)
1.0±0.2Vrms, 1KHz±10%.</td><td>* Shall not exceed the limits given in the detailed spec.</td></tr>
<tr><td>3.</td><td>Q/ D.F. (Dissipation Factor)</td><td>
<table>
<tr><th>Dielectric</th><th>Q/D.F.</th><th>Remark</th></tr>
<tr><td rowspan="2">Class I (C0G)</td><td>Q≥1000</td><td>Cap.≥30pF</td></tr>
<tr><td>Q≥400+20C</td><td>Cap.<30pF</td></tr>
<tr><td rowspan="4">Class II</td><td>D.F.≤2.5%</td><td>X7R items</td></tr>
<tr><td>D.F.≤3.5%</td><td>X7R 0603≥0.047μF, 0805=0.1μF, 1206≥0.47μF</td></tr>
<tr><td>D.F.≤5.0%</td><td>X7R 0603≥0.068μF, 0805>0.1μF
All Y5V items</td></tr>
<tr><td>D.F.≤10.0%</td><td>X7R 0805>0.22μF</td></tr>
</table>
</td></tr>
<tr><td>4.</td><td>Temperature Coefficient</td><td>* With no electrical load.
<table>
<tr><th>T.C.</th><th>Operating Temp.</th></tr>
<tr><td>C0G</td><td>-55~125°C at 25°C</td></tr>
<tr><td>X7R</td><td>-55~125°C at 25°C</td></tr>
<tr><td>Y5V</td><td>-25~85°C at 20°C</td></tr>
</table>
</td><td>
<table>
<tr><th>T.C.</th><th>Capacitance Change</th></tr>
<tr><td>C0G</td><td>Within ±30ppm/°C</td></tr>
<tr><td>X7R</td><td>Within ±15%</td></tr>
<tr><td>Y5V</td><td>Within +30%/-80%</td></tr>
</table>
</td></tr>
<tr><td>5.</td><td>Insulation Resistance</td><td>
<table>
<tr><th>Rated Vol.(V)</th><th>Apply Voltage</th><th>Test Condition</th></tr>
<tr><td>=100</td><td>1 times of U_R</td><td>Max. 120 sec.</td></tr>
<tr><td>100<V≤500</td><td>1 times of U_R</td><td>60 sec.</td></tr>
<tr><td>>500</td><td>500Vdc</td><td>60 sec.</td></tr>
</table>
</td><td>
<table>
<tr><th>Dielectric</th><th>Requirements</th></tr>
<tr><td>Class I</td><td>≥10GΩ or RxC≥500Ω-F, whichever is smaller</td></tr>
<tr><td>Class II</td><td>≥10GΩ or RxC≥100Ω-F, whichever is smaller</td></tr>
</table>
</td></tr>
<tr><td>6.</td><td>Solderability</td><td>* Solder temperature : 235±5°C for (0402~1210).
* Solder temperature : 245±5°C for (1808~2225).
* Dipping time : 2±0.5 sec.</td><td>* 75% min. coverage of all metalized area.</td></tr>
<tr><td>7.</td><td>Dielectric Strength</td><td>
<table>
<tr><th>Rated Vol.(V)</th><th>Condition</th></tr>
<tr><td>≤100</td><td>2.5 times of U_R</td></tr>
<tr><td>100<V≤250</td><td>2.0 times of U_R</td></tr>
<tr><td>250<V≤500</td><td>1.5 times of U_R</td></tr>
<tr><td>=630</td><td>1.2 times of U_R</td></tr>
</table>
* Duration : 1 to 5 sec.
* Charge and discharge current less than 50mA.
</td><td>* No evidence of damage or flashover during test.</td></tr>
<tr><td>8.</td><td>Resistance to Soldering Heat</td><td>* Solder temperature : 260±5°C.
* Dipping time : 10±1 sec.
* Preheating : 120 to 150°C for 1 minute before immerse the capacitor in a eutectic solder.
* Before initial measurement (Class II only) : Perform 150 +0/-10°C for 1 hr and then set for 48±4 hrs at room temp.
* Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).</td><td>* No remarkable damage.
* Cap. Change :
C0G : Within ±2.5% or ±0.25pF, whichever is larger.
X7R : Within ±7.5%.
Y5V : Within ±20%.
* Q/D.F. & I.R. : To meet the initial requirement.
* 25% max. leaching on each edge.</td></tr>
<tr><td>9.</td><td>Temperature Cycle</td><td>* Conduct the five cycles according to the temperatures and time.
<table>
<tr><th>Step</th><th>Temp.(°C)</th><th>Time(min.)</th></tr>
<tr><td>1</td><td>Min. operating temp. +0/-3</td><td>30±3</td></tr>
<tr><td>2</td><td>Room temp.</td><td>2~3</td></tr>
<tr><td>3</td><td>Max. operating temp. +3/-0</td><td>30±3</td></tr>
<tr><td>4</td><td>Room temp.</td><td>2~3</td></tr>
</table>
* Before initial measurement (Class II only) : Perform 150 +0/-10°C for 1 hr and then set for 48±4 hrs at room temp.
* Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).
</td><td>* No remarkable damage.
* Cap. change :
C0G : Within ±2.5% or ±0.25pF, whichever is larger.
X7R : Within ±7.5%.
Y5V : Within ±20%.
* Q/D.F. :
C0G : To meet the initial requirement.
X7R, Y5V : D.F.≤150% of initial requirement.
* I.R. : To meet the initial requirement.</td></tr>
</table>

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2


8. RELIABILITY TEST CONDITIONS AND REQUIREMENTS


No.	Item	Test Condition	Requirements
10.	**Humidity (Damp Heat) Steady State**	* Test temp. : 40±2°C. * Humidity : 90~95%RH. * Test time : 500 +24/-0 hrs. * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).	* No remarkable damage. * Cap. change : C0G : Within ±5.0% or ±0.5pF, whichever is larger. X7R : Within ±12.5%. Y5V : Within ±30%. * Q/D.F. : C0G : Cap.>30pF, Q≥350; 10pF≤Cap.≤30pF, Q≥275+2.5C; Cap.<10pF, Q≥200+10C. X7R, Y5V : D.F.≤200% of initial requirement. * I.R. : ≥1GΩ or RxC≥50Ω-F, whichever is smaller. X7R 100V : ≥1GΩ or RxC≥10Ω-F, whichever is smaller.
11.	**Humidity (Damp Heat) Load**	* Test temp. : 40±2°C. * Humidity : 90~95% RH. * Test time : 500 +24/-0hrs. * To apply voltage : Rated voltage (Max. 500Vdc). * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).	* No remarkable damage. * Cap. change : C0G : Within ±7.5% or ±0.75pF, whichever is larger. X7R : Within ±12.5%. Y5V : Within ±30%. * Q/D.F. : C0G : Cap.≥30pF, Q≥200; Cap.<30pF, Q≥100+10/3C. X7R, Y5V : D.F.≤200% of initial requirement. * I.R. :≥500MΩ or RxC≥25Ω-F, whichever is smaller. X7R 100V : ≥500MΩ or RxC≥5Ω-F, whichever is smaller.
12.	**High Temperature Load (Endurance)**	* Test temp. : C0G, X7R : 125±3°C. Y5V : 85±3°C. Dielectric / Rated Vol.(V) / Apply Voltage: C0G, X7R, Y5V: ≤250 → 2.0 times of U_R; 250<V≤500 → 1.5 times of U_R; =630 → 1.2 times of U_R * Exception items : Rated Vol.(V) / Size / Cap. Range / Apply Voltage: 100: 0603 ≥0.082μF; 0805 ≥0.12μF 200 & 250: 0603 ≥0.082μF; 1210 ≥0.22μF; 1812 ≥0.47μF (Exception items Apply Voltage: 1.5 times of U_R) * Test time : 1000 +24/-0 hrs. * Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).	* No remarkable damage. * Cap. change : C0G : Within ±3.0% or ±0.3pF, whichever is larger. X7R : Within ±12.5%. Y5V : Within ±30%. * Q/D.F. : C0G : Cap.>30pF, Q≥350; 10pF≤Cap.≤30pF, Q≥275+2.5C; Cap.<10pF, Q≥200+10C. X7R, Y5V : D.F.≤200% of initial requirement. * I.R. : ≥1GΩ or RxC≥50Ω-F, whichever is smaller. X7R 100V : ≥1GΩ or RxC≥10Ω-F, whichever is smaller.

著作權所有 信昌電子陶瓷股份有限公司 COPYRIGHT © PROSPERITY DIELECTRICS CO., LTD. ALL RIGHTS RESERVED

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2

8. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

<table>
<tr><th>No.</th><th>Item</th><th>Test Condition</th><th>Requirements</th></tr>
<tr><td>13</td><td>Resistance to Flexure of Substrate</td><td>* The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1mm per second until the deflection becomes 1mm.


Unit : mm</td><td>* No remarkable damage.
<table>
<tr><th>Dielectric</th><th>Cap. Change</th></tr>
<tr><td>Class I (C0G)</td><td>Within ±3.0% or ±2.0pF, whichever is larger</td></tr>
<tr><td>Class II (X7R)</td><td>Within ±12.5%</td></tr>
<tr><td>Class II (Y5V)</td><td>Within ±30%</td></tr>
</table>
(This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test)</td></tr>
<tr><td>14.</td><td>Adhesive Strength of Termination</td><td>* Capacitors mounted on a substrate. A force of 5N(≤0603) or 10N(>0603) applied perpendicular to the place of substrate and parallel the line joining the center of terminations for 10±1 second.

</td><td>* No remarkable damage or removal of the terminations.</td></tr>
<tr><td>15.</td><td>Vibration Resistance</td><td>* Vibration frequency : 10~55 Hz/min.
* Total amplitude : 1.5mm.
* Test time : 6 hrs. (Two hrs each in three mutually perpendicular directions)
* Measurement to be made after keeping at room temp. for 24±2 hrs (Class I) or 48±4 hrs (Class II).</td><td>* No remarkable damage.
* Cap. change and Q/D.F. : To meet the initial spec.</td></tr>
</table>

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2

9. PACKAGE DIMENSION AND QUANTITY

Size	Thickness (mm)	Paper tape		Plastic tape	
		7" reel	13" reel	7" reel	13" reel
0201(0603)	0.30±0.03	15k	70k	-	-
	0.30±0.05	15k	-	-	-
	0.30±0.09	15k	-	-	-
0402(1005)	0.50±0.05	10k	50k	-	-
	0.50 +0.02/-0.05	10k	50k	-	-
	0.50±0.20	10k	-	-	-
0603(1608)	0.50±0.10	4k	-	-	-
	0.80±0.07	4k	15k	-	-
	0.80 +0.15/-0.10	4k	15k	-	-
0805(2012)	0.50±0.10	4k	15k	-	-
	0.60±0.10	4k	15k	-	-
	0.80±0.10	4k	15k	-	-
	0.85±0.10	4k	15k	-	-
	1.25±0.10	-	-	3k	10k
	1.25±0.20	-	-	3k	10k
1206(3216)	0.80±0.10	4k	15k	-	-
	0.85±0.10	4k	15k	-	-
	0.95±0.10	-	-	3k	10k
	1.15±0.15	-	-	3k	10k
	1.25±0.10	-	-	3k	10k
	1.60±0.20	-	-	2k	10k
	1.60 +0.30/-0.10	-	-	2k	9k
1210(3225)	0.85±0.10	-	-	3k	10k
	0.95±0.10	-	-	3k	10k
	1.25±0.10	-	-	3k	10k
	1.60±0.20	-	-	2k	-
	2.00±0.20	-	-	1k	6k
	2.50±0.30	-	-	1k	6k
1808(4520)	1.25±0.10	-	-	2k	10k
	1.60±0.20	-	-	2k	8k
	2.00±0.20	-	-	1k	6k
1812(4532)	1.25±0.10	-	-	1k	5k
	1.60±0.20	-	-	1k	-
	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	3k
	2.80±0.30	-	-	0.5k	-
1825(4563)	1.60±0.20	-	-	1k	-
	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	-
	2.80±0.30	-	-	0.5k	-
2220(5750)	1.60±0.20	-	-	1k	-
	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	-
	2.80±0.30	-	-	0.5k	-
2225(5763)	1.60±0.20	-	-	1k	-
	2.00±0.20	-	-	1k	-
	2.50±0.30	-	-	0.5k	-
	2.80±0.30	-	-	0.5k	-

Unit : pcs

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2

9. PACKAGE DIMENSION AND QUANTITY

9.1. EMBOSSED TAPE DIMENSIONS




Fig. 9.1 The dimension of paper tape




Fig. 9.2 The dimension of plastic tape

Size	0201	0402	0603		0805	
Chip Thickness	0.30±0.03	0.50±0.05 0.50±0.10	0.80±0.07	0.80 +0.15/-0.1	0.80±0.10	1.25±0.10 1.25±0.20
A_0	0.39±0.07	0.70±0.20	1.00 +0.05/-0.10	1.02 +0.05/-0.10	1.50±0.10	<1.65
B_0	0.69±0.07	1.20±0.20	1.80±0.10	1.80±0.10	2.30±0.10	<2.40
T	≤0.50	≤0.80	0.95±0.05	0.97±0.05	0.95±0.05	0.23±0.05
K_0	-	-	-	-	-	<2.50
W	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10
P_0	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
$10xP_0$	40.00±0.10	40.00±0.10	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20
P_1	2.00±0.05	2.00±0.05	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
P_2	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D_0	1.55±0.05	1.55±0.05	1.55±0.05	1.55±0.05	1.55±0.05	1.50 +0.10/-0
D_1	-	-	-	-	-	1.00±0.10
E	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.10
F	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05
Unit :	mm	mm	mm	mm	mm	mm

Size	1206			1210		1812	
Chip Thickness	0.80±0.10	0.95±0.10 1.25±0.10	1.60±0.20 1.60+0.3/-0/1	0.95±0.10 1.25±0.10 1.60±0.20	2.50±0.30	1.25±0.10 1.60±0.20 2.00±0.20	2.50±0.30
A_0	2.00±0.10	<2.00	<2.00	<3.05	<3.10	<3.90	<3.90
B_0	3.50±0.10	<3.60	<3.70	<3.80	<4.00	<5.30	<5.30
T	0.95±0.05	0.23±0.05	0.23±0.05	0.23±0.05	0.23±0.05	0.25±0.05	0.25±0.05
K_0	-	<2.50	<2.50	<2.50	<3.50	<2.50	<3.00
W	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	12.00±0.20	12.00±0.20
P_0	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
$10xP_0$	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.0±0.20	40.00±0.20	40.00±0.20
P_1	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	8.00±0.10	8.00±0.10
P_2	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D_0	1.55±0.05	1.50 +0.10/-0	1.50 +0.10/-0	1.50 +0.10/-0	1.50 +0.10/-0	1.50 +0.10/-0	1.50 +0.10/-0
D_1	-	1.00±0.10	1.00±0.10	1.00±0.10	1.00±0.10	1.50±0.10	1.50±0.10
E	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10
F	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05	5.50±0.05	5.50±0.05
Unit :	mm	mm	mm	mm	mm	mm	mm

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2

9. PACKAGE DIMENSION AND QUANTITY

Size	1825		2220		2225	
Chip Thickness	1.60±0.20 2.00±0.20	2.50±0.30	1.40±0.15 1.60±0.20 2.00±0.20	2.50±0.30	1.60±0.20 2.00±0.20	2.50±0.30
A_0	<6.80	<6.80	<5.80	<5.80	<6.80	<6.80
B_0	<5.30	<5.30	<6.50	<6.50	<6.50	<6.50
T	0.30±0.10	0.30±0.10	0.30±0.10	0.30±0.10	0.30±0.10	0.30±0.10
K_0	<2.50	<3.10	<2.50	<3.10	<2.50	<3.10
W	12.00±0.20	12.00±0.20	12.00±0.20	12.00±0.20	12.00±0.20	12.00±0.20
P_0	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
$10xP_0$	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20	40.00±0.20
P_1	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10
P_2	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D_0	1.50 +0.10/-0	1.50 +0.10/-0	1.50 +0.10/-0	1.50 +0.10/-0	1.50 +0.10/-0	1.50 +0.10/-0
D_1	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10	1.50±0.10
E	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10	1.75±0.10
F	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05	5.50±0.05
Unit :	mm	mm	mm	mm	mm	mm

9.2. REEL DIMENSIONS

Size	0201, 0402, 0603, 0805, 1206, 1210			1808, 1812, 1825, 2220, 2225
Reel size	7”	7”	13”	7”
C	13.0 +0.5/-0.2	13.0 +0.5/-0.2	13.0 +0.5/-0.2	13.0 +0.5/-0.2
W_1	8.4 +1.5/-0	12.4 +2.0/-0	8.4 +1.5/-0	8.4 +1.5/-0
A	178.0 ±0.10	178.0 ±0.10	330.0 ±1.0	178.0 ±0.10
N	60.0 +1.0/-0	80.0 ±1.0	100 ±1.0	60.0 +1.0/-0




Fig. 9.3 The dimension of reel

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2

10. APPLICATION NOTES

STORAGE

To prevent the damage of solderability of terminations, the following storage conditions are recommended :
Indoors under 5 ~ 40°C and 20% ~ 70% RH.
No harmful gases containing sulfuric acid, ammonia, hydrogen sulfide or chlorine.
Packaging should not be opened until the capacitors are required for use. If opened, the pack should be re-sealed as soon as is practicable. Taped product should be stored out of direct sunlight, which might promote deterioration in tape or adhesion performance. The product is recommended to be used within 12 months after shipment and checked the solderability before use.

HANDLING

Chip capacitors are dense, hard, brittle, and abrasive materials. They are liable to suffer mechanical damage, in the form of cracks or chips. Chip Capacitors should be handled with care to avoid contamination or damage. To use vacuum or plastic tweezers to pick up or plastic tweezers is recommended for manual placement. Tape and reeled packages are suitable for automatic pick and placement machine.

PREHEAT


In order to minimize the risk of thermal shock during soldering, a carefully controlled preheat is required. The rate of preheat should not exceed 3°C per second.

SOLDERING

Use middy activated rosin RA and RMA fluxes do not use activated flux. The amount of solder in each solder joint should be controlled to prevent the damage of chip capacitors caused by the stress between solder, chips, and substrate.

a.) Hand soldering :

Fig. 10.1 Hand Soldering Profile



Chip Size	Pre-Heat temp.	ΔT	Max. soldering iron temp.
≤1206	≥150°C	≤150°C	≤350°C
1210~2225	≥150°C	≤130°C	≤280°C


* Soldering iron tip diameter ≤1.0 mm and wattage max. 20W.
* The Capacitors shall be pre-heated and that the temperature gradient between the devices and the tip of the soldering iron.
* The required amount of solder shall be melted on the soldering tip.
* The tip of iron should not contact the ceramic body directly.
* The Capacitors shall be cooled gradually at room temperature after soldering.
* Forced air cooling is not allowed.

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved.

10. APPLICATION NOTES

b.) Reflow soldering :


Fig. 10.2 Reflow soldering profile



For Sn/Ag/Cu Series solder paste (Pb-Free)

c.) Wave soldering :

Fig. 10.3 Wave soldering profile



For Sn/Ag/Cu Series solder paste (Pb-Free)

Soldering conditions :

Class I :

Size Inch (mm)	Temper. Cher.	Capacitance	Condition	
			Wave	Reflow
≤0402 (1005)	All Class I	All	X	O
0603 (1608)	All Class I	All	O	O
0805 (2012)	All Class I	All	O	O
1206 (3216)	All Class I	All	O	O
≥1210 (3225)	All Class I	All	X	O

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved. PDC DCM-003-8.3 Rev 2


10. APPLICATION NOTES

Soldering conditions :
Class II :

Size Inch (mm)	Temper. Cher.	Capacitance	Condition	
			Wave	Reflow
≤0402 (1005)	All Class II	All	X	O
0603 (1608)	All Class II	Cap. <2.2μF	O	O
		Cap. ≥2.2μF	X	O
0805 (2012)	All Class II	Cap. <4.7μF	O	O
		Cap. ≥4.7μF	X	O
1206 (3216)	All Class II	Cap. <4.7μF	O	O
		Cap. ≥4.7μF	X	O
≥1210 (3225)	All Class II	All	X	O

Soldering height :

The solder climbing minimum height is suggesting to 25% of chip thickness or 500um whichever is less.
(Reference from IPC-610E)



版權所有 侵害必究 信昌電子陶瓷股份有限公司 Prosperity Dielectrics Co., Ltd. COPYRIGHT © PROSPERITY DIELECTRICS CO., LTD. ALL RIGHTS RESERVED

COOLING

After soldering, cool the chips and the substrate gradually to room temperature. Natural cooling in air is recommended to minimize stress in the solder joint.

CLEANING

All flux residues must be removed by using suitable electronic-grade vapor-cleaning solvents to eliminate contamination that could cause electrolytic surface corrosion. Good results can be obtained by using ultrasonic cleaning of the solvent. The choice of the proper system is depends upon many factors such as component mix, flux, and solder paste and assembly method. The ability of the cleaning system to remove flux residues and contamination from under the chips is very important.

Copyright © by Prosperity Dielectrics Co., LTD. | All rights reserved.

Unikeyic Electronics

Global Electronic Components Distributor

Click to view pricing, inventory, delivery, and lifecycle information:

PSA:

FEC0805CP-R25G-LRH FEC1008CP-22NG-LRH FEC1008CP-R75G-LRH FM21X102K501PXG FS55X106K101EGG FV31X102K202ECG FV43X102K202EEG FEC0603CP-R33G-LRH FEC0603CP-R27G-LRH FEC1008CP-3R3G-LRH FN31X102K500PXG FS55X106K101EHG FV31X103K102ECG FV43X103K202EGG FEC0603CP-36NG-LRH FV32X103K102EEG FMF25FPJR008-LH FS32X225K500EGG FM32N333J631EGG FN18X224K250PBG FS43X225K101EGG FV31N330J102ECG FV42X102K302EFG FEC0603CP-5N1G-LRH FM55X684K631EGG FN31X474K500EPG FEC0603CP-6N1G-LRH FEC1008CP-24NG-LRH FM32X684K101EFG FM43X224K631EGG